


TORAYFAN® CBE2

Application

- HFFS
- VFFS
- Pouch



TRANSPARENT BARRIER COATED
ONE SIDE HEAT SEALABLE BOPP FILM

Benefits

- Mono-web material to facilitate recyclability
- Ease of processing during printing and lamination
- Wide operating window for HFFS machines
- Enables High Machine Speed in HFFS applications
- Product protection and extended shelf life
- Excellent Aroma Barrier
- Chlorine free film

Typical Values *(These values do not constitute binding specifications)*

Properties	Test Method	Unit	25 µm
Nominal Yield		m ² /kg	44.6
Tensile Strength @ Break MD	ASTM D 882	daN/mm ²	14
Tensile Strength @ Break TD			29
Young's Modulus MD	ASTM D 882	daN/mm ²	320
Young's Modulus TD			630
Elongation @ Break MD	ASTM D 882	%	200
Elongation @ Break TD			58
Heat Shrinkage MD (140°C for 15min)	Internal Method	%	4
Heat Shrinkage TD (140°C for 15min)			1
COF (B/B)	ASTM D1894	Dynamic	0.35
COF (A/A)	ASTM D1894	Dynamic	0.35
Haze (1 sheet)	ASTM 1003	%	5
Heat-seal Strength (B/B) @121°C	Internal Method	g/25mm	550
Seal Initiation Temp: SIT (>200g/25mm)	Internal Method	N/25mm	70°
Wetting Tension – Coated Side	ASTM D2578	Dyne/cm	55
MVTR – 38°C / 90% RH	ASTM F1249	g/m ² /day	2.5
O2 Barrier – 23°C / 0% RH	ASTM D3985	cc/m ² /day	3


Key Features

- Excellent Gas and Moisture Barrier
- Chlorine Free
- Non-moisture sensitive product
- Low Seal Initiation Temperature
- High Seal Strength
- Seals B/B
- Stable Coefficient of Friction

Markets

- Biscuits
- Bakery
- Cereal Bars
- Confectionery
- Nuts
- Dried Foods
- Snacks

Winding Direction



Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Storage & handling conditions
- Any other information about typical values, measuring conditions, tolerances, deliveries...

Torayfan® is a registered trademark of Toray Films Europe SAS - TFE June 2020

DISCLAIMER: This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.